

TECHNICAL DATA INFORMATION

ALKYD TOP COAT RZ - 2131

Product Description

RZ-2131 is a versatile finish coat based on air drying alkyd resin.

Recommended Use

As a finish coat on exterior and interior of steel structures, wood substrates and masonries, previously primed with alkyd primers.

Outstanding Characteristics

- Good gloss and colour retention
 - Excellent spray ability
 - Excellent flexibility
 - Good resistance in mildly to moderate corrosive environments
-

Surface Preparation

The surface must be clean, dry and free from any contamination such as grease, salt and loose paint. Old primed surfaces should be roughened before repainting.

Technical Data

Finish	Gloss
Color	White, gray (Upon request*)
Volume Solids	40 ± 2%
Specific Gravity	1.01 ± 0.03 gr/cm ³
Flash Point	38 °C
Recommended D.F.T.	40 - 60 microns
Theoretical coverage	10-6.66 m ² /lit. 9.9-6.6 m ² /kg
Practical Coverage	Depends on loss factor
Touch dry	4 hrs at 25 °C
Thermal Resistance	Up to 90 °C
Shelf life	12 months at 25 °C

Application Details

Application method	Air/Airless spray, Brush, Roller
Nozzle orifice	0.017"-0.019"
Nozzle pressure	150 bar / 2200 Psi
Application temperature	above 10 °C
Thinner/Cleaner	RZT- 21

Application Procedure RZ-2131

1. Flush all equipment with recommended cleaner before use.
2. Stir the product thoroughly with a power mixer.
3. For conventional spray, thin with no more than 20% of recommended thinner for workability. For airless spray 10% of thinner is normally sufficient.
4. Apply a wet coat by parallel passes. Overlap each pass 50% to avoid bare areas, pinholes or holidays.
5. Double coat all welds, rough spots, sharp edges, rivets, bolts, etc. to ensure proper thickness.
6. Check thickness of dry coating with a non-destructive dry film thickness gauge. Recoat if greater thickness is required.
7. Random pinholes, holidays and small damaged or bare areas can be touched up by brush when the film is dry to touch. Larger areas should be resprayed.
8. In confined areas ventilate with clean air during application and drying until all solvents are removed.
9. Clean all equipment with recommended cleaner immediately after use.

Limitations

Surface temperature must be at least 3°C above dew point.
Relative humidity during application should be less than 80%.
Do not apply coatings under reverse environmental conditions.

Safety

This product is flammable. Keep away from heat and open flame. Keep container closed. Avoid prolonged and repeated contact with skin.

Since improper use and handling can be hazardous to health and cause fire or explosion, safety precautions included with application instructions must be observed during all storage, handling, and use and drying periods.

If used in confined areas:

- circulate adequate fresh air continuously during application and drying.

- Use fresh air masks and explosion proof equipment

- Prohibit all flames, sparks, welding and smoking

- Take precautionary measures against static discharges

Keep away from food products.

Storage and Handling

The products must be stored in accordance with national regulations.

The products should be kept in a cool and well ventilated place protected from heat and direct sunlight. Containers must be kept tightly closed.

Handle with care. Stir well before use.

Remarks

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience.

However we reserve the right to change the given data without notice.

Any recommendation relating to the use of the products is based on data believed to be reliable. It is buyer to satisfy itself of the suitability of the product for its own particular use.

As the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself.

*Technical data is designed for the white, gray, cream and many shades. Some of physical parameters maybe changed for other shades.

RANGUIN ZEREH

Protective Coatings

No.15, Str, 15th Bokharest Ave. Tehran/ Iran
Tel: +98 21 88723676 Fax: +98 21 88716358
<http://www.Ranguinzereh.com>
Email: info@Ranguinzereh.com

Revised Feb 2011
